

SQUARE SPECIFICATION PORCELAIN STONEWARE

MATERIAL

Porcelain stoneware.

Classified in GROUP Bla UGL CON Ev ≤ 0,5%.

Complies with all the requirements of UNI EN 14411 ISO 13006 APP. G standards.

COLOR		SIZES	SURFACE	THICKNESS
DOWNTOWN	V2			
AVENUE	V2			
STREET	V2	MATTE RECTIFIED	MATTE	0.884
WAY	V2	80x80 (32"x32") . 60x120 (23 ⁵⁸ "x48") . 60x60 (23 ⁵⁸ "x23 ⁵⁸ ") . 30x60 (11 ^{7,8} "x23 ⁵⁸ ")	MATTE	9 MM
DISTRICT	V2			
CROSSING	V2			

PROCESS certified according to the ISO 9001 quality standard

Product obtained from exceptionally pure, choice quality raw materials, including light-coloured clays, feldspar fluxes, kaolins, sands and coloured ceramic pigments. Pressing in hydraulic presses allows a pressure of over 500kg/cm2 to be applied to the product, guaranteeing dimensional precision, planarity and high mechanical strength.

The product's colours and patterns are achieved with the innovative Digital Technology.

The materials are fired in single-layer roller kilns at temperatures of over 1,220°C.

GREEN BUILDING: CERTIFIED ENVIRONMENTAL SUSTAINABILITY

The tiles in the Square collection are ideal for eco-sustainable building:

- They are produced in plants which have an EMAS-ISO 14001 certified environmental management system.
- They help to obtain credits for the construction of buildings in accordance with the LEED certification programme.

Size	
Finishes	
Color	Type















SQUARE

















TECHNICAL TABLE PORCELAIN STONEWARE

CONFORMING TO STANDARDS

EN 14411 ISO 13006 ANNEX G GROUP Bla UGL CON Ev $\leq 0.5\%$

	PHYSICAL PROPERTIES	TESTING METHOD	REFERENCE STANDARD			PRODUCT VALUES
				7cm ≤ N < 15 cm		Rectified
			Length and width	(mm) ±0.9	(%) (mm) ±0.6 ±2.0	±0.2 %
	Sizes	EN ISO 10545-2	Thickness	±0.5	±5.0 ±0.5	±5 %
			Linearity	±0.75	±0.5 ±1.5	±0.2 %
			Wedging	±0.75	±0.5 ±2.0	±0.2 %
			Warpage	±0.75	±0.5 ±2.0	±0.2 %
			Appearance: percentage of acceptable tiles, per lot	95 % min.	95 % min.	
	Water absorption %	EN ISO 10545-3	Ev ≤ 0,5%			< 0,1%
	Modulus of rupture		Valore medio 35 N/mm² min.			45 N/mm²
	Breakage resistence	EN ISO 10545-4	sp. > = 7,5 mm: min 1300 N sp. < 7,5 mm: min 700 N			2500 N (9 mm)
0	Scratch resistance	EN ISO 10545-6	175 mm3 max.			Average < 150 mm3
	Thermal expansion coefficient	EN ISO 10545-8	Declared value			6,8 MK ⁻¹
	Thermal shock resistance	EN ISO 10545-9	Pass according to iso 10545-1			* Resistant
茶	Frost resistance	EN ISO 10545-12	Pass according to iso 10545-1			* Resistant
	Resistance to low concentrations of acids and alkali		Declared value			* Resistant
	Resistance to high concentrations of acids and alkali	EN ISO 10545-13	Declared value			* Resistant
	Resistance to domestic chemicals and additi- ves for swimming pools		UB min.			UA
K	Stain resistance of unglazed matte porcelain	EN ISO 10545-14	Declared value			* Resistant
	Friction coefficient (slipperiness)	DIN 51130				Declared value
		DIN 51097				Declared value
		B.C.R.A D.M.236/ 89	If needed			> 0,40 Dry / > 0,40 Wet
		ANSI A326.3				≥ 0,42 Wet

